

**Concrix**<sup>®</sup>  
SA



## PRODUCT DESCRIPTION

Concrix SA is a bicomponent macro synthetic fibre serving as structural concrete reinforcement. The special rough embossing enables an optimum anchoring to the concrete. The increased technical parameters of the concrete can be used for static concrete fibre reinforcement calculation.

## APPLICATIONS

- Precast
- Precast: thin wall elements
- Reduction of plastic shrinkage

## DOSAGE

The recommended dosage für Concrix SA is between 2,0 – 7,5 kg per m<sup>3</sup> of concrete.

## PROPERTIES

Raw material	polyolefin
Density	0,91 kg/dm <sup>3</sup>
Resistance to acids/alkali	inert
Composition	bicomponent, rough embossed fibre.
Form	macrofibre
Length	25,0 mm, tolerance +/- 1,5 mm
Diameter	0,50 mm
Tensile strength	≈ 620 N/mm <sup>2</sup>
E-Modul	≈ 11 000 N/mm <sup>2</sup>
Softening point	≈ 150°
Colour	Yellow
Number of fibres per kg	≈ 200 000

## MIXING

The addition of Concrix SA may increase the consistency of the concrete.

It is recommended to check the consistency of the concrete prior to the start of the project. If an adaption of the consistency is necessary, plasticizers should be added.

Before emptying the ready-mix truck on the jobsite, the fibre concrete should be mixed at maximum revolution speed of the ready-mix truck for about 2 minutes.

## PACKAGING

- Article-Nr.
- 775014 : 4,0 kg plastic bag loose

## STORAGE

Under cover, dry, protected from moisture and humidity.

## CONFORMITY

- Norm EN 14889-2 System 1, Class II
- DIBt Zulassung : Allgemeine bauaufsichtliche Zulassung : Nr. Z-3.73.2040 „Plastic Shrinkage“
- EPD/Environmental Product Declaration ISO 14025 and EN-15804: Nr. 1.1.00438.2023

Contec Fiber AG does not have any control over production processes using Concris SA. Therefore, Contec Fiber AG declines any liability for the associated end products.

The information contained in this datasheet represents our best knowledge, know-how and expertise at the time of creation. Contec Fiber AG assumes no liability for the information or related advice.